

MICRO MR3

| | |
|------------|--|
| Product | Micro Agglomerated |
| Class | MR3 Granule size: 0,5 – 1 mm |
| Marking | Ink and/or fire |
| Packing | Polyethylene bags with SO ₂ |
| Expedition | Cardboard boxes in plastic pallet |
| Intend use | Still wines |



| Tests and units | Specifications / Tolerance | Method |
|------------------------------|--|------------------|
| Dimensions and ovality | L ± 0,5 mm Ø: ± 0,5 mm O: ≤ 0,5 mm | ISO 9727-1:2007 |
| Specific weight | 290 ± 40 Kg/m ³ | ISO 9727-2:2007 |
| Humidity | 6% +/- 2% | ISO 9727-3:2007 |
| Extraction force | 12 - 30 daN | ISO 9727-5:2007 |
| Liquid seal | 2,5 bar | ISO 9727-6:2007 |
| Peroxide residues | < 0 mg / cork stopper | NP 4502-2011 |
| Sensorial analysis | Without deviations | ISO 22308-1:2021 |
| 2,4,6 - Tricloroanisol (TCA) | Not Detectable (≤ 0,5 ng/L) | ISO 20752:2023 |



Technical Specifications according to the International Code of Practice for Cork Stoppers

MICRO MR5

| | |
|------------|--|
| Product | Micro Agglomerated |
| Class | MR3 Granule size: 0,5 – 1 mm |
| Marking | Ink and/or fire |
| Packing | Polyethylene bags with SO ₂ |
| Expedition | Cardboard boxes in plastic pallet |
| Intend use | Still wines |



| Tests and units | Specifications / Tolerance | Method |
|------------------------------|--|------------------|
| Dimensions and ovality | L ± 0,5 mm Ø: ± 0,5 mm O: ≤ 0,5 mm | ISO 9727-1:2007 |
| Specific weight | 290 ± 40 Kg/m ³ | ISO 9727-2:2007 |
| Humidity | 6% +/- 2% | ISO 9727-3:2007 |
| Extraction force | 12 - 30 daN | ISO 9727-5:2007 |
| Liquid seal | 2,5 bar | ISO 9727-6:2007 |
| Peroxide residues | < 0 mg / cork stopper | NP 4502-2011 |
| Sensorial analysis | Without deviations | ISO 22308-1:2021 |
| 2,4,6 - Tricloroanisol (TCA) | Not Detectable (≤ 0,5 ng/L) | ISO 20752:2023 |



Technical Specifications according to the International Code of Practice for Cork Stoppers

MICRO MRA

| | |
|------------|--|
| Product | Micro Agglomerated |
| Class | MRA Granule size: 0,5 – 1,0 mm |
| Marking | Ink and/or fire |
| Packing | Polyethylene bags with SO ₂ |
| Expedition | Cardboard boxes in plastic pallet |
| Intend use | Still wines |



| Tests and units | Specifications / Tolerance | Method |
|------------------------------|--|------------------|
| Dimensions and ovality | $L \pm 0,5 \text{ mm} \mid \phi: \pm 0,5 \text{ mm} \mid O: \leq 0,5 \text{ mm}$ | ISO 9727-1:2007 |
| Specific weight | $290 \pm 40 \text{ Kg/m}^3$ | ISO 9727-2:2007 |
| Humidity | 6% +/- 2% | ISO 9727-3:2007 |
| Extraction force | 12- 30 daN | ISO 9727-5:2007 |
| Liquid seal | 2,5 bar | ISO 9727-6:2007 |
| Peroxide residues | < 0 mg/cork stopper | NP 4502-2011 |
| Sensorial analysis | Without deviations | ISO 22308-1:2021 |
| 2,4,6 - Tricloroanisol (TCA) | $\leq 1,0 \text{ ng/L}$ | ISO 20752:2023 |



Technical Specifications according to the International Code of Practice for Cork Stoppers.